

## CLAIMS

What is claimed is:

- 1009375510211021
- Sub  
a1
1. A magnetic-field sensor device comprising:
    - at least two electrodes;
    - an insulating layer separating said at least two electrodes; and
    - at least one layer of chemically-synthesized magnetic nanoparticles disposed between said at least two electrodes.
  2. The magnetic-field sensor device of claim 1, wherein said at least two electrodes comprise a magnetic material.
  3. The magnetic-field sensor device of claim 1, wherein at least one of said at least two electrodes comprises a magnetic material.
  4. The magnetic-field sensor device of claim 1, wherein at least one of said at least two electrodes is one of a non-magnetic metal and a semiconductor.
  5. The magnetic-field sensor device of claim 1, wherein said chemically-synthesized magnetic nanoparticles range in size between 2 nm and 20 nm in diameter.

1 6. The magnetic-field sensor device of claim 1, wherein said chemically-synthesized  
2 magnetic nanoparticles are oriented with a magnetic-moment orientation parallel to a direction of  
3 current flow through said chemically-synthesized magnetic nanoparticles.

1 7. The magnetic-field sensor device of claim 1, wherein said chemically-synthesized  
2 magnetic nanoparticles are oriented with a magnetic-moment orientation perpendicular to a  
3 direction of current flow through said chemically-synthesized magnetic nanoparticles.

1 8. The magnetic-field sensor device of claim 1, wherein said at least one layer of  
2 chemically-synthesized magnetic nanoparticles comprises at least one chemically-synthesized  
3 magnetic nanoparticle.

1 9. The magnetic-field sensor device of claim 1, wherein said chemically-synthesized  
2 magnetic nanoparticles comprise elements comprising one of Co, Fe, Ni, Mn, Cr, Nd, Pr, Pt, Pd,  
3 Ho, Gd, Eu, Er, Re, Rh, an intermetallic compound of said elements, a binary alloy of said  
4 elements, a ternary alloy of said elements, an oxide comprising one of Fe, Co, Ni, Mn, and Cr,  
5 and a mixed oxide combining at least one of Fe, Co, Ni, Mn, and Cr, with at least one of La, Sr,  
6 Ba, and Cu.

1 10. The magnetic-field sensor device of claim 1, wherein said insulating organic layer  
2 separates one chemically-synthesized magnetic nanoparticle layer from another chemically-  
3 synthesized magnetic nanoparticle layer.

1 11. A magnetic-field sensor device comprising:  
2 at least two electrodes;  
3 an insulating layer separating said at least two electrodes; and  
4 at least one layer of chemically-synthesized magnetic nanoparticles disposed between said  
5 at least two electrodes;

6 wherein said at least two electrodes comprise a magnetic material.

12. The magnetic-field sensor device of claim 11, wherein at least one of said at least two electrodes comprises a magnetic material.

13. The magnetic-field sensor device of claim 11, wherein at least one of said at least two electrodes is one of a non-magnetic metal and a semiconductor.

14. The magnetic-field sensor device of claim 11, wherein said chemically-synthesized magnetic nanoparticles range in size between 2 nm and 20 nm in diameter.

15. The magnetic-field sensor device of claim 11, wherein said chemically-synthesized magnetic nanoparticles are oriented with a magnetic-moment orientation parallel to a direction of current flow through said chemically-synthesized magnetic nanoparticles.

1 16. The magnetic-field sensor device of claim 11, wherein said chemically-synthesized  
2 magnetic nanoparticles are oriented with a magnetic-moment orientation perpendicular to a  
3 direction of current flow through said chemically-synthesized magnetic nanoparticles.

1 17. The magnetic-field sensor device of claim 11, wherein said at least one layer of  
2 chemically-synthesized magnetic nanoparticles comprises at least one chemically-synthesized  
3 magnetic nanoparticle.

1 18. The magnetic-field sensor device of claim 11, wherein said chemically-synthesized  
2 magnetic nanoparticles comprise elements comprising one of Co, Fe, Ni, Mn, Cr, Nd, Pr, Pt, Pd,  
3 Ho, Gd, Eu, Er, Re, Rh, an intermetallic compound of said elements, a binary alloy of said  
4 elements, a ternary alloy of said elements, an oxide comprising one of Fe, Co, Ni, Mn, and Cr,  
5 and a mixed oxide combining at least one of Fe, Co, Ni, Mn, and Cr, with at least one of La, Sr,  
6 Ba, and Cu.

1 19. The magnetic-field sensor device of claim 10, wherein said insulating organic layer  
2 separates one chemically-synthesized magnetic nanoparticle layer from another chemically-  
3 synthesized magnetic nanoparticle layer.

1 20. A method of forming a magnetic-field sensor device, said method comprising:  
2 depositing a first electrode onto a substrate;  
3 depositing an electrically insulating layer on said first electrode;

4 removing a portion of said electrically insulating layer to expose a region of said first  
5 electrode;

6 depositing at least one layer of chemically-synthesized nanoparticles on said electrically  
7 insulating layer and said exposed region of said first electrode; and

8 depositing a second electrode on said chemically-synthesized nanoparticles and said  
9 electrically insulating layer.

Sub  
21. The method of claim 20, wherein said substrate comprises one of a conducting material  
and a non-conducting material.

22. The method of claim 20, wherein said first and second electrodes comprise an electrically  
conducting and magnetic material.

23. The method of claim 20, further comprising depositing a layer of magnetic material on  
said substrate.

24. The method of claim 20, wherein said chemically-synthesized nanoparticles comprise  
elements comprising one of Co, Fe, Ni, Mn, Cr, Nd, Pr, Pt, Pd, Ho, Gd, Eu, Er, Re, Rh, an  
intermetallic compound of said elements, a binary alloy of said elements, a ternary alloy of said  
elements, an oxide comprising one of Fe, Co, Ni, Mn, and Cr, and a mixed oxide combining at  
least one of Fe, Co, Ni, Mn, and Cr, with at least one of La, Sr, Ba, and Cu.

1 25. A method of forming a magnetic-field sensor device, said method comprising:  
2 depositing a first electrode onto a substrate;  
3 depositing an electrically insulating layer on said first electrode;  
4 depositing a second electrode on said electrically insulating layer;  
5 removing a portion of said electrically insulating layer to create an empty space;  
6 depositing at least one layer of chemically-synthesized nanoparticles in said empty space;  
7 and  
8 removing said substrate.

9 26. The method of claim 25, wherein said substrate comprises one of a conducting material  
10 and a non-conducting material.

11 27. The method of claim 25, wherein said first and second electrodes comprise an electrically  
12 conducting and magnetic material.

13 28. The method of claim 25, wherein said chemically-synthesized nanoparticles comprise  
14 elements comprising one of Co, Fe, Ni, Mn, Cr, Nd, Pr, Pt, Pd, Ho, Gd, Eu, Er, Re, Rh, an  
15 intermetallic compound of said elements, a binary alloy of said elements, a ternary alloy of said  
16 elements, an oxide comprising one of Fe, Co, Ni, Mn, and Cr, and a mixed oxide combining at  
17 least one of Fe, Co, Ni, Mn, and Cr, with at least one of La, Sr, Ba, and Cu.